

6 Mil Anti-Graffiti Xtra



MECHANICAL PROPERTIES

Thickness	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	83 %
Visible Light Reflected	11 %
Ultra Violet Block	93 %
Total Solar Energy Reflected	10 %
Total Solar Energy Transmitted	73 %
Total Solar Energy Absorbed	15 %
Shading Coefficient	0.92
Solar Heat Gain Coeff. (G-value)	0.80
Total Solar Energy Rejected	19 %

