

4 Mil Clear Xtra



MECHANICAL PROPERTIES

Thickness	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	86 %
Visible Light Reflected	9 %
Ultra Violet Block	99.5 %
Total Solar Energy Reflected	8 %
Total Solar Energy Transmitted	73 %
Total Solar Energy Absorbed	19 %
Shading Coefficient	0.90
Solar Heat Gain Coeff. (G-value)	0.78
Total Solar Energy Rejected	20 %

