

XtraZone

5 Mil Silver 20 Xtra



MECHANICAL PROPERTIES

Thickness	5 mil
Tensile Strength at Break	28,500 PSI
Break Strength	145 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	16 %
Visible Light Reflected	62 %
Ultra Violet Block	99.7 %
Total Solar Energy Reflected	66 %
Total Solar Energy Transmitted	12 %
Total Solar Energy Absorbed	22 %
Glare reduction	82 %
Shading Coefficient	0.21
Solar Heat Gain Coeff. (G-value)	0.18
Total Solar Energy Rejected	82 %

