

Safety Zone

5 Mil Silver 60, Exterior SR

MECHANICAL PROPERTIES

Thickness	5 mil
Tensile Strength at Break	28,500 PSI
Break Strength	145 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch



OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	57%
Visible Light Reflected	22%
Ultra Violet Block	99%
Total Solar Energy Reflected	24%
Total Solar Energy Transmitted	42%
Total Solar Energy Absorbed	34%
Shading Coefficient	0.59
Total Solar Energy Rejected	50%

